



TYPICAL CROSS SECTION

Notes

1. **Use when existing asphalt is temporary on trench reinstatement.**
STAGE Ia Sawcut ; **STAGE Ib** Excavation and drain laying ; **STAGE Ic** Backfill ; **STAGE Id** Tack coat ; **STAGE II** layer of asphalt.
2. **Tack Coat**
 A tack coat shall be applied to the approved base course surface on which the hot mix asphalt is to be placed. Tack coat shall consist of cationic bitumen emulsion and shall be applied to a dry surface, free from puddles. Tack coat shall be sprayed in a uniform film over the entire shared trail and vehicle turnaround surface as detailed on the Drawings. Unless otherwise directed, the application rate for bitumen emulsion tack coat shall be 0.15 to 0.3litres/m2 (60% Bitumen content) or 0.3 to 0.6 litres/m2 (30% bitumen content) in accordance with current VicRoads Standards.
 Tack coat is to set and become tacky prior to application of the hot mix asphalt.

Council require that all road openings follow the conditions detailed on the back of road opening permits. All back filled trenches are to be maintained in a safe condition and sealed with p.c.m. until council contractor is able to seal the trench/hole.

	Standard Drawing Title		Standard Drawing No.	Rev:
	ASPHALT TEMPORARY REINSTATEMENT		BCC203	A
			Page 1 of 1	
		Scale	Approved Manager Engineering Services	
		1:20		
		References to:	Date: 18-Dec-08	